


CLAIMS

1. A polyamide resin composition comprising polyamide resin and swelling mica treated with a polyether compound, wherein the polyether compound is represented by general formula (1):



(wherein -A- represents -O-, -S-, -SO-, -SO<sub>2</sub>-, -CO-, an alkylene group having 1 to 20 carbon atoms, or alkylidene group having 6 to 20 carbon atoms; and R<sup>1</sup>, R<sup>2</sup>, R<sup>3</sup>, R<sup>4</sup>, R<sup>5</sup>, R<sup>6</sup>, R<sup>7</sup>, and R<sup>8</sup> may be the same or different and each represent a hydrogen atom, a halogen atom, or a monovalent hydrocarbon group having 1 to 5 carbon atoms).

2. The polyamide resin composition of claim 1, further comprising at least one of a styrene resin, an anhydride-containing olefin copolymer, and a carbon compound.

3. The polyamide resin composition of claim 1, further comprising a styrene resin.

4. The polyamide resin composition of claim 1, further

comprising an anhydride-containing olefin copolymer.

5. The polyamide resin composition of claim 4, wherein the anhydride-containing olefin copolymer is obtained by  
5 copolymerization or graft reaction of olefin or an olefin copolymer with an alicyclic dicarboxylic anhydride having a cis double bond in the ring or an  $\alpha,\beta$ -unsaturated dicarboxylic anhydride.

10 6. The polyamide resin composition of claim 4, wherein the content of the anhydride-containing olefin copolymer in the polyamide resin composition is in the range of 1 to 30 percent by weight.

15 7. The polyamide resin composition of claim 1, further comprising a carbon compound.


8. The polyamide resin composition of claim 7, wherein the carbon compound is in the form of particles.

20

9. The polyamide resin composition of claim 7, wherein the carbon compound is fibrous.

10. The polyamide resin composition of any one of claims  
25 1 to 9, wherein the polyether compound is represented by

general formula (2):



(wherein A, R<sup>1</sup>, R<sup>2</sup>, R<sup>3</sup>, R<sup>4</sup>, R<sup>5</sup>, R<sup>6</sup>, R<sup>7</sup>, and R<sup>8</sup> are the same as above; R<sup>9</sup> and R<sup>10</sup> may be the same or different and each represent a divalent hydrocarbon group having 1 to 5 carbon atoms; R<sup>11</sup> and R<sup>12</sup> may be the same or different and each represent a hydrogen atom or a monovalent hydrocarbon group having 1 to 20 carbon atoms; m and n each represent the number of oxyalkylene repeating units; and 2 ≤ m + n ≤ 50).

10

11. The polyamide resin composition of any one of claims 1 to 10, wherein the ratio of the swelling mica having an equivalent circular diameter [D] of 300 nm or less in the composition is 20% or more.

15

12. The polyamide resin composition of any one of claims 1 to 11, wherein the average of the equivalent circular diameter [D] of the swelling mica in the polyamide resin composition is 500 nm or less.

20

13. The polyamide resin composition of any one of claims

1 to 12, wherein the average layer thickness of the swelling mica in the polyamide resin composition is 50 nm or less.

14. The polyamide resin composition of any one of claims  
5 1 to 13, wherein the maximum layer thickness of the swelling mica in the polyamide resin composition is 200 nm or less.

15. The polyamide resin composition of any one of claims  
1 to 14, wherein the number [N] of particles per unit weight  
10 ratio of the swelling mica in the polyamide resin composition is 30 or more.

16. The polyamide resin composition of any one of claims  
1 to 15, wherein the average aspect ratio (layer  
15 length/layer thickness) of the swelling mica in the polyamide resin composition is 10 to 300.

17. The polyamide resin composition of any one of claims  
1 to 16, the content of the swelling mica in the polyamide  
20 resin composition is in the range of 0.5 to 30 percent by weight.

18. The polyamide resin composition of claim 1 or 2,  
prepared by mixing these components.

19. A method for making a polyamide resin composition, comprising melt-mixing the components of the polyamide resin composition set forth in claim 1 or 2.

5 20. A molded resin article entirely or partially composed of the polyamide resin composition according to one of claims 1 to 18.

21. The molded resin article according to claim 20 used  
10 in automobile parts.